

**ARTICOLO**  
*Article*

# Raso Fluo

CARATTERISTICHE TECNICHE  
*Technical properties*

| TIPO DI PROVA<br><i>type of test</i>         |                                                     | UNITA'<br><i>unit</i>              | LONG.<br><i>along</i> | TRASV.<br><i>across</i> | METODO<br><i>test method</i>    |
|----------------------------------------------|-----------------------------------------------------|------------------------------------|-----------------------|-------------------------|---------------------------------|
| CARICO DI ROTTURA<br><i>tensile strenght</i> |                                                     | N/5cm                              | 200 ± 50              | 150 ± 50                | ISO 1421:2016                   |
|                                              | ALLUNGAMENTO A ROTTURA<br><i>extension at break</i> | %                                  | 20 ± 5                | 50 ± 5                  | ISO 1421:2016                   |
|                                              | RESISTENZA ALLA LACERAZIONE<br><i>tear strenght</i> | N                                  | 6 ± 1                 | 6 ± 1                   | UNI EN ISO 4674-1:2017 metodo B |
|                                              | ADESIONE<br><i>peel adhesion</i>                    | N/cm                               | 5 ± 2                 | 5 ± 2                   | UNI EN ISO 2411:2018            |
| FONDAMENTALI<br><i>basic</i>                 | SPESSORE<br><i>thickness</i>                        | mm                                 | 0,80 ± 0,10           |                         |                                 |
|                                              | PESO<br><i>weight</i>                               | g/m <sup>2</sup>                   | 310 ± 25              |                         |                                 |
|                                              | ALTEZZA<br><i>width</i>                             | cm                                 | 140                   |                         |                                 |
|                                              | LUNGHEZZA DEL ROTOLO<br><i>roll length</i>          | m                                  | 50                    |                         |                                 |
|                                              | COMPOSIZIONE<br><i>composition</i>                  | poliestere<br><i>polyester</i>     | %                     | 4 ± 2                   |                                 |
|                                              |                                                     | viscosa<br><i>viscose</i>          | %                     | 22 ± 2                  |                                 |
|                                              |                                                     | poliuretano<br><i>polyurethane</i> | %                     | 74 ± 2                  |                                 |

|                                              |      | COLORE N°<br><i>code number</i> | COLORE<br><i>colour</i>            | GRADO (SCALA DEI BLU)<br><i>grade (blue wool standard)</i> | METODO<br><i>test method</i> |
|----------------------------------------------|------|---------------------------------|------------------------------------|------------------------------------------------------------|------------------------------|
| SOLIDITA' ALLA LUCE<br><i>light fastness</i> | F284 |                                 | verde fluo<br><i>green fluo</i>    | 2-3 scuro<br><i>2-3 darker</i>                             | UNI EN ISO 105-B02           |
|                                              |      |                                 | fuoxia fluo<br><i>fuoxia fluo</i>  | 3-4 ingiallito<br><i>3-4 yellowing</i>                     |                              |
|                                              | F285 |                                 | rosa fluo<br><i>pink fluo</i>      | 2 scuro e ingiallito<br><i>2 darker-yellowing</i>          |                              |
|                                              |      |                                 | blu fluo<br><i>blue fluo</i>       | 3-4 scuro e ingiallito<br><i>3-4 darker-yellowing</i>      |                              |
|                                              | F286 |                                 | arancio fluo<br><i>orange fluo</i> | 2 scuro<br><i>2 darker</i>                                 |                              |
|                                              |      |                                 | giallo fluo<br><i>yellow fluo</i>  | 2-3 scuro<br><i>2-3 darker</i>                             |                              |
|                                              | F287 |                                 |                                    |                                                            |                              |
|                                              |      |                                 |                                    |                                                            |                              |
|                                              | F288 |                                 |                                    |                                                            |                              |
|                                              |      |                                 |                                    |                                                            |                              |

Rev.6

data revisione scheda 02/04/2025

gg/mm/aaaa

revision date 02/04/2025

day/month/year



The mark of  
responsible forestry

Prodotti Certificati FSC® disponibili su richiesta  
FSC® Certified products available on demand